

Specialized Fire Bricks : Zircon

Product	A.P (%)	B.D (gm/cm ³)	C.C.S (kg/cm ²)	RUL Ta (°C)	Al ₂ O ₃ (%)	ZrO ₂ (%)	Fe ₂ O ₃ (%)	Primary Raw Material
VRPL-ZIR 63	20	3.60	600	1600		63.0	0.5	Zircon Sand
VRPL-ZIR 65	17	3.70	800	1700	1.0	65.0	0.3	High Purity Zircon Sand
VRPL- ZM 4831	16	3.05	1000	1700	48.0	30.0	0.5	Fused AZS/Zircon/Alumina
VRPL- ZM 5725	15	3.10	1200	1700	56.0	24.0	0.5	Fused AZS/Zircon/Alumina
VRPL- ZM 6010	17	2.90	800	1650	60.0	10.0	0.8	Andalusite/Zircon
VRPL- ZM 7020	18	3.00	800	1700	68.0	18.0	0.3	Fused AZS/Zircon/Fused Alumina